

- 6 -

WHAT IS CLAIMED IS:

1. A sheet material for wrapping metal goods, in order to protect said metal goods from corrosion, comprising:
5 (a) a woven scrim having an inner side and an outer side;
(b) a polyolefin film laminated on said inner side of said scrim, said film comprising:
10 (i) 0.5-15% by weight of a contact corrosion inhibitor;
and
(ii) 0.1-0.9% by weight of a volatile corrosion inhibitor.
15
2. A sheet material according to claim 1 further comprising a polyolefin film laminated on said outer side of said scrim.
- 20 3. A sheet material according to claim 1 or 2 wherein said scrim comprises polyolefin tapes.
4. A sheet material according to claim 3 wherein said scrim comprises high density polyethylene.
25
5. A sheet material according to claim 3 wherein said scrim is polypropylene.
6. A sheet material according to claim 3 wherein said
30 scrim comprises 4-16 tapes per inch in the machine direction and 2-16 tapes in the cross direction.

- 7 -

7. A sheet material according to claim 6 wherein said scrim has a weight in the range of 30-400 grams per square meter.
- 5 8. A sheet material according to any one of claims 1-7 wherein said inner polyolefin film has a thickness in the range of 0.5-3.0 mils.
9. A sheet material according to claim 8 wherein said
10 inner polyolefin film comprises low density polyethylene.
10. A sheet material according to claim 8 wherein said inner polyolefin film comprises a blend of low density polyethylene and linear low density polyethylene.
- 15 11. A sheet material according to claim 8 wherein said inner polyolefin film comprises polypropylene.
12. A sheet material according to claim 2 wherein said
20 outer film has a thickness in the range of 0.5-3.0 mils.
13. A sheet material according to claim 2 wherein said outer polyolefin film comprises low density polyethylene.
- 25 14. A sheet material according to claim 2 wherein said outer polyolefin film comprises a blend of low density polyethylene and linear low density polyethylene.
15. A sheet material according to claim 2 wherein said
30 outer polyolefin film comprises polypropylene.